



gloveon Avalon

Biodegradable, Nitrile Exam Gloves Powder Free, Standard Cuff

Help improve the environment with GloveOn Avalon biodegradable gloves. Designed to break down normal nitrile gloves in landfill settings, these gloves will take years rather than decades to completely biodegrade. Our unique formulation maintains the high levels of strength and flexibility you'd expect in a nitrile glove, while only allowing the biodegradation process to start once in landfill conditions. Feel confident that GloveOn Avalon will give you the protection you need and help you do your bit for the environment.



Physical Dimensions	
Length (mm)	≥ 230
Palm Thickness (mm)	0.07 ± 0.02
Finger Thickness (mm)	0.10 ± 0.02
Physical Properties	
	Before Ageing
Tensile Strength (MPa)	≥ 18
Elongation (%)	≥ 500
Inspection Levels & AQL	
	Inspection Level
Watertightness	G1
Physical Dimensions	S2
Tensile Strength	S2
Visual Inspection (Major)	S4
Visual Inspection (Minor)	S4
Particulate Residue	N = 5

REORDER CODE

BDG33XS	X-SMALL
BDG33SS	SMALL
BDG33MM	MEDIUM
BDG33LL	LARGE
BDG33XL	X-LARGE

FEATURES

- Biodegrades in landfill conditions
- Fingertip textured • Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested • Ambidextrous
- Standard cuff • Violet blue colour

PACKAGING

200 gloves per box for XS to L
180 gloves per box for XL
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 164563, FDA 510(k), MDR 2017/745, REACH, ROHS Directive 2002/95/EC, EU 10/2011, EC 1935/2004, EU 2016/425

STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124, ASTM D6978, ASTM D5526, ASTM D5511, EN ISO 374-1 (Type C), EN 374 part 2, 4 & 5, EN 16523-1, EN 420, EN 455 part 1, 2 & 3, EN 1186, EN 13130, CEN/TS 14234, ISO 10993 part 5, 10 & 11

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 151891B - Rev 1)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	22.2 Minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Tosopar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	66.1 Minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Avalon nitrile glove at 22.2 minutes and 66.1 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Chemical	EN 374-1:2016 + A1:2008 Permeation Level	EN 374-4:2013 Mean Degradation (%)
K 40% Sodium Hydroxide	6	-63.5
P 30% Hydrogen Peroxide	1	18.0
T 37% Formaldehyde	5	14.2

Supplied by Imbros
+61 3 6216 1500
info@imbros.com.au
imbros.com.au

